

Hydrophobic Polyurethane Grout Cartridge Application

Product description

Everseal Flex Foam is a custom-formulated flexible hydrophobic polyurethane waterstop packaged in two-component cartridges. The convenient cartridge package allows the product to be used for leaking cracks and joints in residential and commercial basements, garages and parking structures. The cartridge system is suitable for repairs in confined spaces where pump injection is not practical.

Everseal Flex Foam is dispensed by using standard, two-component caulking guns equipped with static tube mixers. Hand, battery or air-operated guns are acceptable. No premixing of additional components is required.

Table 1: Physical properties of uncured materials

| | Everseal Flex Foam | | Measurement | Test method |
|--------------------------|--------------------|---------------|----------------------|-------------|
| | Part A | Part B | | |
| Color | pale yellow | Brown | | visual |
| Specific gravity | 1.04 | 1.044 | | ASTM D-891 |
| Viscosity at 77°F (25°C) | 195 | 170 | centipoises | ASTM D-4878 |
| Storage stability | 12 | 12 | months | |
| Corrosiveness | non-corrosive | non-corrosive | | |
| Flash point | 390 (199) | > 300 (>149) | Fahrenheit (Celsius) | |
| DOT regulations | | | | |
| Hazard class | not regulated | not regulated | | |

Table 2: Physical properties of cured materials

| | Everseal Flex Foam | Measurement | Test method |
|-------------------------|--------------------|-------------|-------------|
| Tensile strength | 55 | psi | ASTM D-412 |
| Elongation | 140 | percent | ASTM D-412 |
| Die-C tear | 8 | pli | ASTM D-624 |
| Pot life at 77°F (25°C) | 10 | minutes | |
| Shrinkage by weight | 1-2 | percent | in-house |
| Shrinkage by volume | 2-12 | percent | in-house |
| Density | 60 | pcf | in-house |
| Hazard level | | | |
| Toxicity | non-toxic | | |

Note: These values were generated while simulating a situation where Everseal Flex Foam was applied under pressure similar to typical field condition applications.

Site preparation

The temperature of the wall may alter the reaction time of Everseal Flex Foam when it is injected. Colder walls and concrete will extend the reaction time. Warmer walls will shorten the reaction time. The reaction can be accelerated by heating Everseal Flex Foam. Our recommended application temperature is between 55°F to 90°F (12.8°C to 32.2°C). See the tables to the right.

Precautions

This material is intended to be used by trained professionals with the proper equipment. The following safety measures are recommended:

- Wear protective gloves, clothing, goggles, hearing protection for noise reduction and hard hats for falling debris.
- Do not eat, drink or smoke while in active contact with these materials.
- Avoid skin contact.
- Wash hands thoroughly with soap and cool water. Never wash the skin with a solvent.
- Anyone experiencing difficulty breathing when working with these materials or showing an allergic reaction should seek fresh air immediately and consult a physician if symptoms persist.

Depending on the scope of the project, it may be advisable to consult a manufacturer's representative during installation.

Material storage

Cartridges should be stored above 60°F (15°C) and below 120°F (48°C). Open cartridges should be used quickly to avoid the material gelling in the cartridge or static mix nozzle. Refer to the material safety data sheets (MSDS) for further information regarding these materials.

All spills of Everseal Flex Foam should be disposed by absorbing the grout into an inert material and then transferring the mixture to an open top drum. Do not seal the waste drums for 24 hours to allow the Everseal Flex Foam to react completely. Dispose of waste material in accordance with state and local regulations.

Packaging

Everseal Flex Foam is available in kits consisting of 6, two- component cartridges; Nozzles and nuts are available.

WARRANTY The information contained in this document is to assist customers in determining whether our products are suitable for their applications. Our products are intended for sale to industrial and commercial customers. The customer must inspect and test our products before use, and satisfy themselves as to the contents and suitability. Nothing herein shall constitute a warranty, expressed or implied, including any warranty of merchantability or fitness, nor is protection from any law or patent to be inferred. All patent rights are reserved. The exclusive remedy for all proven claims is replacement of our materials, and in no event shall we be liable for special, incidental or consequential damages.