

## Product description

Everseal Surface Paste Green is a structural adhesive specifically designed to adhere wood to concrete. These components react quickly at room temperature to form crosslinked polymers that are stronger than many of the bonded substrates.

- Designed to adhere ports and seal concrete cracks
- Best dispensed in dual cartridges and mixed by hand, apply with a trowel.
- Works well in situations requiring speed and strength

## Properties

- 2-3 minute initial set
- Bond strength typically stronger than the substrate
- 20-30 minutes ready for injecting
- Low, virtually no odor

**Table 1: Physical properties of uncured materials**

	<b>Everseal Surface Paste</b>	<b>Part A</b>	<b>Part B</b>
Mix Ratio	1:1 by volume and volume		
Appearance		Green	Tan
Solids Content		100%	100%
Flash Point		>300(150)	>300(150)
Weight per Volume		10.98(1.32)	10.55(1.27)
Viscosity; cps@ 77F (25C)		10-30Kcps	10-30Kcps
Solids	100 percent		
Corrosiveness	Non-corrosive		
Flash point	390 (199)	degrees Fahrenheit (Celsius)	

**Curing Physical Properties**

Gel Time	2 minutes
Trixtropy	4-6 minutes
Injection Ready	30 minutes
Full Cure	24 Hours

**Cured Physical Properties**

Accelerate Cure	10 minutes @ 200F
Hardness, Shore D	62
Young's Modulus, psi(MPa)	14,000 (96.5)
Elongation, %	80
Tear Resistance, lbs./in	335
Solids	100 Percent
Corrosiveness	Non-corrosive
Flash point	390 (199)

**Disclaimer of Warranty**

All statements, technical information and recommendations herein are based on tests believed to be reliable. BUT THE ACCURACY OR COMPLETENESS THEREOF IS NOT GUARANTEED AND THE FOLLOWING IS MADE IN LIEU OF ALL WARRANTIES, EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR PURPOSE. Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Before using, user shall determine the suitability of the product for its intended use and user assumes all risk and liability whatsoever in connection therein. NEITHER SELLER NO MANUFACTURER SHALL BE LIABLE EITHER IN CONTRACT FOR ANY LOSS OR DAMAGE, DIRECT, INCIDENTAL, OR CONSEQUENTIAL, ARISING OUT OF THE USE AND OR THE INABILITY TO USE THE PRODUCT. No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by officers of seller and manufacturer.